



AIRCOLOR COBRE

H2

VERSION: 121212
Page: 1/2

COPPER PAINT

DEFINITION

AIRCOLOR COBRE is an enamel composed of copper pigments. Use as a primer to protect areas to be welded. In interiors can be used as a finishing coat, for exteriors we recommend topcoating with clearcoat.




PHYSICAL CHARACTERISTICS

Nature:	Ketone	
Colour:	Copper	
	Aerosol	Cobre
Specific weight:	0,8 kg/l at 20°C	1 kg/l at 20°C
Appearance:	Satin	
Propellant:	GLP C3-C4	
Aerosol pressure:	3 bar at 20°C	
Dry film thickness:	15 microns 2 coats	
Yield:	8 m ² /aerosol	
VOC:	616 g/l	650 g/l
Solid content:	22 %	35 %
Copper content:	66% over dry film	



SURFACE PREPARATION

PROCESS		Steel	Electrozinc-coated
	P80	✓	✓
	DA93	✓	✓

APPLICATION METHOD

	 cm	
1	20	1

DRYING TIMES

	
10°C	10'
20°C	5'
30°C	3'

REMARKS

Shake the aerosol before use for 1 minute after hearing the sound of the mixer.
Protect the areas that will not be painted.

EQUIPMENT CLEANING

After use clean the nozzle by turning the aerosol upside down and spray until only gas will emerge.

SAFETY

Follow instructions of product label. For more information check the Safety Data Sheet. Compliant with the National Statutory Regulation for Health and Safety at Work and Waste Disposal.

STORAGE

Store the product in a ventilated place far from direct exposure to sunlight. Keep between +5°C and +30°C.

GUARANTEE

In unopened original packaging, one year from manufacturing date.

For any technical information contact with our Customer Attention Service or our Technical Department.

ROBERLO SA declines any responsibility due to an incorrect use of the product.

SUGGESTION:

To conduct easier it is recommended to await welding until the product is completely dry.