

LIGHTWEIGHT FIBREGLASS PUTTY

DEFINITION

FUTURA GLASS is a lightweight polyester putty reinforced with glass fibre for the repair of chassis, of highly innovative conception. It can be applied to those surfaces which require the maximum resistance and adherence.

Due to this special formulation, **FUTURA GLASS** is a much softer and more flexible putty than other fibreglass putties, which allows a great ease of application.

FUTURA GLASS fulfils VOC limitation legislation, for what is an Environmentally respectful product.

A principal advantage is the fact that its composition minimizes the appearance of pinholes which may appear after the application, therefore eliminating one of the stages of the repair process in comparison with other fibreglass putties.

A better finish, greater ease of sanding and reduction of process times are aspects previously unknown in a fibreglass putty; we therefore present **FUTURA GLASS** to you as the dawn of a new concept.

PHYSICAL CHARACTERISTICS

Nature:	Unsaturated polyester
Colour:	Light blue
Specific weight:	1,2 kg/l at 20°C
VOC:	6 g/l
	Mixing Application

AUXILIARY PRODUCTS

Hardener PBO

SUITABLE SURFACES

It may be applied on steel, aluminium, galvanised and polyester surfaces.




When maximum protection is required apply on epoxy primer.

Do not apply on thermoplastic finishes and Wash Primers.




SURFACE PREPARATION




1 - Identify surface.

2 - Process:





PROCESS		Steel	Aluminium	Galvanised	Polyester UP-GFK
	P80	✓	✓	✓	✓
	P150	✓	✓	✓	✓
	DA93	✓	✓	✓	✓

1 - APPLICATION

	 WEIGHT		
10°C	100:3	7'	30'
20°C		5,5'	20'
30°C		4'	15'

 TIME
5 min
 DISTANCE
80 cm
 MAX. T
80°C

2 - SANDING

	 ORBIT		
INITIAL	7 – 5 mm	P150	P100
FINAL	5 – 3 mm		P180

REMARKS

Do not add more hardener than specified. Mix thoroughly.
It must be isolated before applying finish coating.
Polyester putties will not harden at temperatures under +5°C.

EQUIPMENT CLEANING

Clean putty knives with a cleaning thinner before the product hardens.

SAFETY

Follow instructions of product label. For more information check the Safety Data Sheet.
Compliant with the National Statutory Regulation for Health and Safety at Work and Waste Disposal.

STORAGE

Store the product in a ventilated place far from direct exposure to sunlight. Keep between +5°C and +30°C.

GUARANTEE

In unopened original packaging, one year from manufacturing date.

SUGGESTION:

Futura Glass is ideal as a filling putty for the Tunning sector since its first low specific weight adds little weight to the vehicle.

For any technical information contact with our Customer Attention Service or our Technical Department.
ROBERLO SA declines any responsibility due to an incorrect use of the product.