

T-905 Matting Agent

COMPARATIVE TABLE WITH DIFFERENT LEVELS OF GLOSS

Examples with D-990 Colour RAL 7011

Thickness applied → 50-60 microns

Mixture ratio → (D-990 + T-905)
2:1 in volume with Hardener 90 STD

	% Gloss Air dried	% Gloss Dried 30' at 70°	Visual appreciation
Without T-905	96 %	96 %	GLOSSY
+ 10% T-905	92 %	90 %	SEMI-GLOSSY
+ 20% T-905	88 %	87 %	SEMI-SATIN
+ 40% T-905	70 %	80 %	SATIN
+ 60% T-905	50 %	65 %	SATIN
+ 80% T-905	30 %	41 %	SEMI-MATT
+ 100% T-905	14 %	21%	MATT

SAFETY

Follow instructions of product label. For more information check the Safety Data Sheets. Compliant with the National Statutory Regulation for Health and Safety at Work and Waste Disposal.

STORAGE

Store the product in a ventilated place far from direct exposure to sunlight. Keep between +5°C and +30°C.

SHELF LIFE

In unopened original packaging, one year from manufacturing date.

*For any technical information contact with our Customer Attention Service or our Technical Department.
ROBERLO SA declines any responsibility due to an incorrect use of the product.*