



PRIMANYL 2120

C29VERSION: 200910
Page: 1/2

WASH PRIMER

DEFINITION

PRIMANYL 2120 is an all purpose primer with two clear distinguishing functions: 1, Will guarantee good adhesion properties and 2. Will protect metal from corrosion.

PRIMANYL 2120 is a chromate and lead free product.



Due to its excellent adhesion, it is recommended for painting galvanized and aluminum surfaces.

Re-coatable with 2k primers and any other paints except nitrosynthetic, chlorinated rubber and epoxy.
The application of polyester putties on this product is not recommended.




PHYSICAL CHARACTERISTICS

Nature:	Vinyl modified		
Colour:	White, Green		
Appearance:	Matt		
Specific weight:	1,0-1,1 kg/l at 20°C		
Dry film thickness:	10 µm	1 coat	
VOC:	710 g/l	Mixing application 2004/42/EC - IIB (c)(780)(710)	
Yield:	12-14 m ² /l	10 µm	








SURFACE PREPARATION

PROCESS		Aluminium	Galvanised	Paint OEM
	P240	√	√	√
	DA93	√	√	√





MIXING RATIO

PRIMANYL 2120			
	1:1 Volume	20'-24"	8h
Hardener 2120	100:80 Weight	F/4 at 20°C	

APPLICATION METHOD

					
	1,3-1,5	3	15 - 20	1	5'
	1,3-1,5	2	10	1	5'

DRYING TIMES

			
20°C	5'	10'	30'

EQUIPMENT CLEANING

Clean with a cleaning thinner before the product hardens.

SAFETY

Follow instructions of product label. For more information check the Safety Data Sheet. Compliant with the National Statutory Regulation for Health and Safety at Work and Waste Disposal.

STORAGE

Store the product in a ventilated place far from direct exposure to sunlight. Keep between +5°C and +30°C.

GUARANTEE

In unopened original packaging, one year from manufacturing date.

These products are for professional use only. The Safety Data Sheet should be consulted before use and the precautionary warnings on the product packaging should be observed. Its correct use, according to its purpose and respecting its technical and security data, provided in these documents, is the sole and exclusive responsibility of the user. ROBERLO S.A.U declines any liability due to the incorrect use of any product.

The information included in this documentation is based on our scientific and technical knowledge on the date of its issuance. ROBERLO reserves the right to modify and/or discontinue all or part of the information at any time and without prior notice. It is the user's responsibility to verify the update of the information. The latest version of this document replaces all previous versions.

All clauses contained herein apply to any future changes or modifications.
For any additional technical information please consult with our Customer Service or our Technical Department.

SUGGESTION:

On galvanised steel
Primanyl 2120 acts as an
adhesion promoter and
also over bare metal as
an adhesion promoter
and anticorrosive.