

ELECTROSTATIC ADDITIVE

DESCRIPTION

- The Electrostatic Additive has been designed to adjust the resistivity of the Disolac industry coatings system to the characteristics of the electrostatic application equipment used.
- Decrease the resistivity of the coating.

CHARACTERISTICS OF ELECTROSTATIC ADDITIVE

| | |
|-----------------|------------------|
| Specific weight | 0,9 kg/l at 20°C |
|-----------------|------------------|

MIXING RATION ON DISOLAC COLOUR (A COMPONENT)

| | SOLID | METALLIC | SOLID/METALLIC | SOLID/METALLIC |
|-------------------------------------|--------------------------|----------|----------------|----------------|
| | % Electrostatic Additive | | | |
| PUR 800-G PUR 800-S PUR 800-M | 2-3% | 1-2% | | |
| PUR 840-G PUR 840-S | | | 3-4% | |
| PUR 840-M | | | | 4-5% |

REMARKS

- An excess of Electrostatic Additive, the resistivity could decrease to zero.
- Follow recommendations for use and safety carefully of the electrostatic application equipment manufacturer.

SAFETY

- Follow instructions of product label.
- For more information check the Safety Data Sheets.
- Complaint with the National Statutory Regulation for Health and Safety at Work and Waste Disposal.



STORAGE

- Store the product in a ventilated place far from direct exposure to sunlight.
- Keep between +5°C and +30°C.

SHELF LIFE

- One year in unopened original packaging.

ANNEX – MESURING EQUIPMENT / RESISTIVITY

| | |
|---------------|---------|
| RANSBURG (MΩ) | 0,3-0,6 |
| GRACO (MΩ) | 38-80 |
| KREMLIN (MΩ) | 30-64 |
| CECA (MΩ) | 5-11 |
| SAMES (MΩ) | 18-38 |
| WAGNER (KΩ) | 150-330 |

*For any technical information contact with our Customer Attention Service or our Technical Department.
ROBERLO SA declines any responsibility due to an incorrect use of the product.*

