

SINT 300

DEFINITION

Fast drying satin paint with good through drying times. It is specially suitable for metallic structures and concrete. It has great resistance that makes it suitable to be used in swimming pools.

The product must be applied in installations that comply with Directive 1999/13/EC.

- The mixing ratio of the Base/Binder is 20/80 in Weight.

PHYSICAL CHARACTERISTICS OF THE PAINT








Nature:	Chlorinated
Appearance:	Satin (75-80 at 60°)
Specific weight:	1,1-1,3 kg/l at 20°C
Solid content:	54-61 % Weight
Solids by volume (binder):	42 ± 2 %
Solids by volume (ready to use):	32 ± 2 %
Dry film thickness:	50-60 microns (2 coats)
Theoretical yield:	7-8 m ² /l

SUBSTRATE AND PREPARATION

New substrates: Apply over vinyl, alkyd, epoxy or polyurethane primers




Old paints: Sand and degrease (Orbit P360/P400)

MIXING RATIO AND APPLICATION METHOD

SINT 300 : Thinner MV						
	100:25-30 volume	20"-23" F/4 20°C	1,3-1,5	2-3	2	5' 20°C

SINT 300

DRYING TIMES

			THROUGH DRY
20°C	5'-10'	30'-40'	2h-2h15'

- Oven drying is not recommended.
- Maximum physical-chemical resistance is obtained after 15 days.

REMARKS

Recommended to be used in ventilated spray booth at 20°C.

EQUIPMENT CLEANING

Use a cleaning thinner before the pot life has expired.

SAFETY

Follow instructions of product label. For more information check the Safety Data Sheets. Compliant with the National Statutory Regulation for Health and Safety at Work and Waste Disposal.

STORAGE

Store the product in a ventilated place far from direct exposure to sunlight. Keep between +5°C and +30°C.

SHELF LIFE

In unopened original packaging, one year from manufacturing date.

*For any technical information contact with our Customer Attention Service or our Technical Department.
ROBERLO SA declines any responsibility due to an incorrect use of the product.*