

TEROSON MS 9220

November 2014

PRODUCT DESCRIPTION

TEROSON MS 9220 provides the following product characteristics:

Technology	MS [®] - Polymer
Product Type	Adhesive
Components	One-component
Cure	Humidity
Application	Assembly
Appearance	Black
Consistency	Pasty, Thixotropic
Odor	Odorless

TEROSON MS 9220 is a one component adhesive with high sag resistance, based on MS-Polymer. The material cures by reaction with humidity to an elastic product. The skin formation and curing times are dependent on humidity and temperature, and the curing time also depends on joint depth. By increasing the temperature and humidity, the reaction time can be reduced; low temperatures as well as low humidity retard the process. TEROSON MS 9220 is free of solvents, isocyanates, silicones and PVC, and has only a weak odour (after curing it is odourless). It demonstrates good adhesion to many substrates. The material demonstrates good resistance to UV-light and can therefore be used for exterior applications.

Application Areas:

TEROSON MS 9220 is used in the areas:

- vehicle body manufacture
- bus manufacture
- vehicle body build-ups
- caravan
- ship and boat building

for elastic bonding without primer and high quality sealing on metallic surfaces (including galvanized metal sheets and aluminium) or painted surfaces. TEROSON MS 9220 is also fitted for bonding glass, ceramic surfaces and most plastics, except Teflon, PE, PP and blends with these polymers. For this reason trials are recommended prior to bonding of plastics. After matching of the materials to be bonded a high adhesion strength is obtained.

TECHNICAL DATA

Colour:	black
Odour:	odourless
Density, g/cm ³ :	approx. 1.4
Consistency:	thixotropic paste

Miscellaneous:

Skin formation time, min*:	approx. 6
Tack-free time, min.:	20 to 30
Cure rate, mm/24 hrs:	approx. 3.5
Shore-A-hardness (DIN 53505):	approx. 60
Tensile strength (acc. to DIN 53504), MPa:	approx. 3.3
Shear strength (DIN EN 1465), MPa:	approx. 4.4
Substrates:	painted sheet metal
Layer thickness, mm:	0.2
Cross head speed, mm/min:	10
Volume change (acc. to DIN 52451), %:	<2
Application temperature, °C:	15 to 35
In service temperature range, °C:	-40 to +100
Short exposure (up to 1 h), °C:	120

* DIN 50014 standard climate: 23°C, 50% relative air humidity

DIRECTIONS OF USE

Preliminary statement:

Prior to application it is necessary to read the **Material Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed.

Pre-Treatment:

The substrates must be clean, dry and grease free. For pretreatment TEROSON VR 20 and TEROSON D are suitable.

General remarks:

Low material temperatures of the sealant will lead to an increase of viscosity, resulting in a lower extrusion rate. This can be avoided by bringing the sealant up to room temperature prior to application. If substrates are too cold temperature may fall below dew point causing condensation. This can be avoided by bringing the substrates up to room temperature in time.

Application:

TEROSON MS 9220 can directly be applied from cartridges employing standard air or hand operated guns. In case of compressed air application a pressure of 2-5 bar is required, depending on nozzle aperture and application speed. When applying TEROSON MS 9220 in closed rooms, it is important to ventilate well during the curing process.

Cleaning:

For cleaning application equipment contaminated with uncured TEROSON MS 9220 we recommend the use of cleaner TEROSON D.

Cured material can only be removed mechanically.

STORAGE**Shelf life:**

Frost-Sensitive	No
Recommended storage temperature, °C	10 to 25
Shelf-life	12 months

Disclaimer**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage: [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

Henkel AG & Co. KGaA

D-40191 Düsseldorf, Germany

Phone: +49-211-797-0

www.henkel.com

Henkel Central Eastern Europe GmbH

A-1030 Wien, Austria

Phone: +43-1711-040

www.henkel.com

Henkel & Cie AG

CH-4133 Pratteln, Switzerland

Phone: +41-61-825-7000

www.henkel.com

